Brazilian Journal of Chemical Engineering

ISSN 0104-6632 Printed in Brazil www.abeq.org.br/bjche

Vol. 31, No. 03, pp. 591 - 601, July - September, 2014 dx.doi.org/10.1590/0104-6632.20140313s00002813

# MgO NANOPARTICLES AS ANTIBACTERIAL AGENT: PREPARATION AND ACTIVITY

Zhen-Xing Tang<sup>1,2\*</sup> and Bin-Feng  $Lv^2$ 

<sup>1</sup>Department of Food Science, Phone: 86-571-88320317, Anqing Vocational & Technical College, 246003, Anqing, Anhui, China. E-mail: tangzhenxing@126.com
<sup>3</sup>Date Palm Research Center, King Faisal University, P. O. Box 420, Al-Hasa 31982, Saudi Arabia.

(Submitted: June 30, 2013; Revised: September 22, 2013; Accepted: September 23, 2013)

**Abstract** - Bacterial pollution is a great risk for human health. Nanotechnology offers a way to develop new inorganic antibacterial agents. Nano-inorganic metal oxide has a potential to reduce bacterial contamination. MgO is an important inorganic oxide and has been widely used in many fields. Many studies have shown that MgO nanoparticles have good antibacterial activity. Therefore, in this paper, the main synthesis methods, antibacterial activity and antibacterial mechanisms of MgO nanoparticles are reviewed.

Keywords: MgO nanoparticles; Synthesis; Antibacterial activity; Antibacterial Mechanism.

## **INTRODUCTION**

Bacterial contamination continues to draw public attention. It is estimated that approximately 48 million cases of pathogenic diseases occur in the United States (Morris 2011; Jin and He, 2011). Therefore, in order to solve this problem, it is highly necessary to develop effective antimicrobial agents to control the bacterial population (Kumar et al., 2008; Li et al., 2006). Generally, antibacterial agents can be categorized as organic or inorganic antibacterial agents. Organic antibacterial agents such as organic acids, essential oils, bacteriocins and enzymes have been widely studied. However, they have some shortcomings, such as low resistance to processing conditions, which limit their applications. As a result, inorganic antibacterial agents have attracted much interest for bacterial control (Fang et al., 2006; Jung et al., 2008). The main advantages of inorganic antibacterial agents, compared to organic antibacterial agents, are the improved stability under harsh processing conditions (Hewitt et al., 2001; Makhluf et al., 2005). Presently, some of the inorganic antibacterial materials, in

particular inorganic metal oxides such as TiO<sub>2</sub>, ZnO, MgO and CaO, have been studied (Huang *et al.*, 2000; Sawai *et al.*, 1995, 1998, 1999, 2000; Sawai, 2003). Among the studied inorganic metal oxides, ZnO, MgO and CaO are of particular interest because they are not only stable under harsh process conditions, but also generally regarded as safe materials to human beings (Stiomenov *et al.*, 2002; Sundrarajan *et al.*, 2012). Additionally, they have antimicrobial activity without photo-activation, compared to TiO<sub>2</sub> that requires photo-activation (Stiomenov *et al.*, 2002; Fang *et al.*, 2006; Jones *et al.*, 2008; Roselli *et al.*, 2003; Manna, 2012).

Recently, nanosciences and nanotechnology has been leading to a technological revolution in the world, which is concerned with materials with significantly novel and improved physical, chemical and biological properties (Wani and Shah, 2012; Sundrarajan *et al.*, 2012). In this regard, nanoparticles are recognized as antibacterial agents due to their size, structure, and surface properties (Raghupathi *et al.*, 2011). Thus, nanotechnology offers a way to improve the activity of inorganic antibacterial agents. Metal oxide nano-

<sup>\*</sup>To whom correspondence should be addressed

particles such as ZnO, MgO and CaO have been investigated as inorganic antibacterial agents (Roselli *et al.*, 2003; Stoimenov *et al.*, 2002; Shi *et al.*, 2012; Tang *et al.*, 2012).

MgO is an important inorganic material with a wide band-gap (Al-Gaashani et al., 2012). It has been used in many applications such as catalysis, catalyst supports, toxic waste remediation, refractory materials and adsorbents, additive in heavy fuel oils, reflecting and anti-reflecting coatings, superconducting and ferroelectric thin films as the substrate, superconductors and lithium ion batteries, etc (Ouraipryvan et al., 2009; Mirzaei and Davoodnia, 2012). In medicine, MgO is used for the relief of heartburn, sore stomach, and for bone regeneration (Bertinetti et al., 2009; Boubeta et al., 2010). Recently, MgO nanoparticles have shown promise for application in tumor treatment (Di et al., 2012). MgO nanoparticles also have considerable potential as an antibacterial agent. Therefore, in this review, the main synthesis methods, antibacterial activity and antibacterial mechanisms of MgO nanoparticles are discussed.

# PREPARATION OF MgO NANOPARTICLES

Many methods, including sol-gel method, hydrothermal method, mechanochemical method, vapor phase method, microemulsion method etc., have been used for the preparation of MgO nanoparticles. The morphology and sizes of MgO nanoparticles can be controlled by adjusting the processing conditions (Kumar and Kumar, 2008; Selvam *et al.*, 2011). In this section, three methods, including the sol-gel method, hydrothermal method and microemulsion method, are mainly discussed. Some examples of the preparation of MgO nanoparticles are shown in Table 1.

#### Sol-Gel Method

For the sol-gel process method, a magnesium alkoxide  $Mg(OR)_2$  is hydrolyzed in an alcohol solvent to yield the hydroxide, which is followed by hydrolysis, condensation, polymerization reactions

and thermal dehydration (Lopez *et al.*, 1998; Stark *et al.*, 1996; Znaidi *et al.*, 1996; Koper *et al.*, 1997). The use of magnesium alkoxides such as magnesium methoxide and magnesium ethoxide has been discussed in a few reports (Bokhimi, 1995; Portillo *et al.*, 1996; Jung *et al.*, 2003 a, b; Stengl *et al.*, 2003). Many factors such as temperature, time, pH, catalytic agent for gel formation, and the environmental conditions can significantly affect the characteristics of the nanoparticles (Klabunde *et al.*, 1996; Bokhimi *et al.*, 1995). The advantages of the sol–gel method are simplicity, cost effectiveness, high yield of nanoparticles, and low reaction temperature (Jiu *et al.*, 2007).

Stengl *et al.* (2004) described the preparation of magnesium hydroxide aerogels on the basis of the hydrolysis and condensation reactions of the alkoxide. Magnesium oxide aerogels with surface areas of  $\sim 537 \text{ m}^2/\text{g}$  were obtained. Kim *et al.* (2005) studied the effect of acetic acid on the stability of the precursor magnesium methoxide and crystallization behavior of sol-gel-derived MgO nanoparticles. Kumar and Kumar (2008) synthesized MgO nanoparticles using magnesium nitrate and oxalic acid as precursors. This process involved gel formation, dehydration of magnesium oxalate, and decomposition of magnesium oxalate at different temperatures (500-1000 °C). MgO nanoparticles with average size 6.5-73.5 nm were obtained.

However, the sol-gel method can usually cause the agglomeration of MgO nanoparticles, which hinders its wide application (Zhou et al., 2011; Ouraipryvan et al., 2009). Therefore, it is required to develop a surfactant-mediated synthesis method to overcome this limitation. Many polymeric surfactants have been used in the sol-gel method (Esmaeili et al., 2009; Zhou et al., 2011; Meshkani and Rezaei, 2009, 2010; Jin et al., 2009). Mastuli et al. (2012) prepared MgO nanoparticles using the sol-gel route assisted with cetyltrimethylammonium bromide (CTAB) as a surfactant to reduce the agglomeration of the particles. The results showed that the use of CTAB in the sol-gel method gave MgO nanoparticles with less agglomeration. CTAB could provide a good control of the morphology and size of MgO nanoparticles.

Table 1: Examples of the preparation of MgO nanoparticles.

Preparation method	Precursors	Particle Size/nm	References
Hydrothermal	$NH_3.H_2O, Mg(NO_3)_2$	50-100	Jiu et al. (2001)
Hydrothermal	$Na_2CO_3$ , $Mg(NO_3)_2$	30	Zhang (1999)
Hydrothermal	NH <sub>3</sub> .H <sub>2</sub> O, MgCl <sub>2</sub>	62	Zhu et al. (2001)
Hydrothermal	MgCl <sub>2</sub> , NaOH	15	Suzuki et al. (1992)
Hydrothermal	Urea, $MgCl_2$	15-20	Chen et al. (2002)
Sol-gel	$Mg(OC_2H_6)_2, H_2O$	30	Alvarado et al. (2000)
Sol-gel	$Mg(NO_3)_2$ , stearic acid	20-50	Xu (2006)

#### **Hydrothermal Method**

Generally, the hydrothermal method may be one of the simplest methods to prepare MgO nanoparticles. Typically, the magnesium salts and base solution are prepared in water. Afterwards, the magnesium salt solution is mixed with base solution by varying the molecular ratio of Mg<sup>2+</sup>/OH<sup>-</sup>. Finally, the precipitate is washed and calcined in an oven. Factors such as magnesium precursors, reactant solvents and reaction conditions play an important role in controlling the morphology and size of MgO nanoparticles (Sutradhar *et al.*, 2011; Mel'gunov *et al.*, 2003; Reddy *et al.*, 2010; Fedorov *et al.*, 2007).

Huang et al. (2005) studied the controllable preparation of MgO nanoparticles by the hydrothermal method. The results showed that the particle size increased with the increase of calcination temperature. Through adjusting the concentration of  $Mg(NO_3)_2$ , reaction temperature and calcination conditions, MgO nanoparticles with different particle sizes were obtained. Camtakan et al. (2012) synthesized MgO nanoparticles by the hydrothermal method using MgCl<sub>2</sub> and NaOH as precursors. The results revealed that the as-prepared MgO nanoparticles had an average diameter of about 24 nm. Recently, Sundrarajan et al. (2012) prepared MgO nanoparticles by the hydrothermal method using magnesium nitrate and sodium hydroxide as precursors and soluble starch as a stabilizing agent. MgO nanoparticles with different sizes could be obtained by controlling different calcination temperature. Calcination temperature could significantly affect the morphology and size of MgO nanoparticles. Similarly, Krishnamoorthy et al. (2012) prepared MgO nanoparticles using magnesium nitrate and sodium hydroxide as precursors and cellulose as a stabilizing agent. The size of the as-prepared MgO nanoparticles was in the range from 10 to 30 nm.

At present, in order to reduce reaction time and cost, many new processes have been developed for

preparing MgO nanoparticles. The microwave-assisted hydrothermal method has been attracting significant attention because it has advantages such as the short reaction time, narrow size distribution, high purity of the prepared particles, and high yield rate of nanoparticles (Aslan and Geddes, 2009). Moreover, it is potentially more cost effective compared to conventional synthesis methods (Nishioka et al., 2011a,b; Bhatte et al., 2012). In the microwave-assisted hydrothermal method, the precursor solution is irradiated by a microwave source. The efficient energy transfer results in a rapid heating process (Parida and Parija, 2006; Moghaddam and Saeisian, 2007). Polyol solvents such as ethylene glycol are extremely suitable for this method because of their relatively high dipole moment and loss factor. Takahashi (2007) reported the preparation of cubeshaped MgO nanoparticles by the microwave-assisted hydrothermal method. Recently, Selvam et al. (2011) synthesized MgO nanoparticles from magnesium and urea as precursors by the microwave-assisted route. Compared to nanoparticles prepared by the conventional method, MgO nanoparticles obtained by the microwaveassisted method had higher surface area ( $63.56 \text{ m}^2/\text{g}$ ).

Currently, the sonochemical method has been extensively used to generate nanoparticles (Gandhi et al., 2011). Ultrasonic waves can stimulate certain novel chemical processes such as nucleation, growth, and collapse of cavitation bubbles formed in the liquid through localized hot spots in the liquid of extremely high temperature (~ 2,700 °C) and pressure (~1,000 atm). Gandhi et al. (2011) obtained MgO nanoparticles with sizes from 5 to 10 nm through this ultrasound-assisted hydrothermal method. In our group, MgO nanoparticles were obtained by a sonication-assisted hydrothermal method (Tang et al., 2012; Tang and Shi, 2008). By controlling calcination conditions and reaction parameters, MgO nanoparticles with different sizes were obtained (Figs. 1 and 2).



Figure 1: Transmission electron microscopy (TEM) image of MgO nanoparticles (Tang et al., 2012)

Brazilian Journal of Chemical Engineering Vol. 31, No. 03, pp. 591 - 601, July - September, 2014



# Figure 2: X-Ray diffraction (XRD) of MgO nanoparticles (Tang et al., 2012)

#### **Micro-Emulsion Method**

There are some reports on the synthesis of MgO nanoparticles using surfactants. Khairallah and Glisenti (2007) reported that non-ionic surfactants like Brij-56 and TX-100 could produce particles with surface areas of 22  $m^2/g$  and 65  $m^2/g$  with crystallite sizes 16 and 18 nm, respectively. However, in these syntheses the precursor is usually heated along with the surfactant to get the oxide, which probably leads to the decrease in surface area. In order to solve this problem, the micro-emulsion method has been used (Ganguli et al., 2010; Eastoe et al., 2006; Ranjan et al., 2009; Vaidya et al., 2008). The size of the reverse micelles dispersed homogeneously in the microemulsion is in the nano-regime and thus they can be used as nano-reactors to synthesize nanomaterials. The morphology and size of the particles can be adjusted by the proper choice of the surfactant and a number of parameters, which include the concentration of water, surfactant, and nature of non-polar phase. Ganguly et al. (2011) synthesized MgO nanoparticles by the micro-emulsion method. The results showed that monodisperse and uniform MgO nanoparticles 8-10 nm in size with a surface area  $\sim 108 \text{ m}^2/\text{g}$  were obtained.

# ANTIBACTERIAL ACTIVITY OF MgO NANOPARTICLES

Many analytical methods have been used to evaluate the antibacterial activity of MgO nanoparticles. One of the most used methods is the broth dilution method, followed by colony count, which plates serial culture broth dilutions containing bacteria and MgO nanoparticles incubated at proper conditions in suitable agar medium. Many reports have shown that the antibacterial activity of MgO nanoparticles is size-dependent. Huang et al. (2005) reported that antibacterial activity was increased with the decrease of the particle size of MgO. A relationship between the bactericidal efficacy against B. subtilis ATCC 9372 and the particle size of nano-MgO was demonstrated. For particles in the size range  $\sim$  45-70 nm, the bactericidal efficacy of nano-MgO increased slowly with decreasing particle size. Below ~ 45 nm however, the bactericidal efficacy showed a much stronger dependence on particle size. Makhluf et al. (2005) demonstrated that small MgO nanoparticles had an efficient antibacterial activity towards Escherichia coli (E. coli) and Staphylococcus aureus (S. aureus). Small, electron-dense black dots could be observed in the cytoplasm of MgO-nanoparticle-treated bacteria (Fig. 3). In the *E. coli* case, a low-density area in the

middle of the cell was observed (Fig. 3d). These MgO particles within the cells were suggested to have been re-formed from individual MgO nanoparticles that penetrated the bacterial cell wall and cell membrane. The results revealed a clear size effect, where the amount of killed bacteria was strongly dependent on particle size. Sundrarajan et al. (2012) investigated the effect of MgO nanoparticles size on the antibacterial activity. The results indicated that small-sized MgO nanoparticles had better antibacterial activities towards both gram positive (S. aureus) and gram negative (E. coli) bacteria. Furthermore, MgO nanoparticles had more activity towards gram positive bacteria compared to gram negative bacteria. Generally, the specific surface area of MgO nanoparticles increases as the size of the nanoparticles decreases. The increase in surface area determines the potential number of reactive groups on the particle surface, which are expected to show high antibacterial activity (Nel et al., 2006; Pal et al., 2007).



**Figure 3:** The effect of MgO nanoparticles on the ultra-structure of *S. aureus* and *E. coli* cells (reproduced with permission from Makhluf *et al.*, 2005) TEM of *S. aureus* untreated cells (a), and treated cells (b). *E. coli* untreated cells (c) and treated cells (d). Magnification 60 K. Scale bar: 0.5 µm.

In addition to the particle size-dependent antibacterial effect of MgO nanoparticles, some studies have indicated that MgO nanoparticles have dosagedependent antibacterial activity. Sawai (2003) reported that the activity of MgO nanoparticles against *E. coli* increased with the increase of MgO concentration. Jin and He (2011) found that higher MgO nanoparticle concentrations resulted in greater bacterial inactivation. An approximate seven log unit reduction in *E. coli* O 157: H7 was achieved by an 8 mg/mL MgO nanoparticle treatment at 24 h. At 7 h, the anti *E. coli* O157: H7 activity of MgO nanoparticles was dependent on its concentration, as in the case of low inoculum levels. The treatment with 3 mg/mL or higher MgO nanoparticles significantly reduced cell concentrations to undetectable levels after 24 h at room temperature, indicating 3 mg/mL MgO nanoparticles would be enough to kill all cells. Shrivastava et al. (2007) reported the preparation of silver nanoparticles in the range of 10-15 nm with increased stability and enhanced anti-bacterial potency. The antibacterial effect was dose dependent. An et al. (2011) and Zhang et al. (2011) also found that high MgO nanoparticle concentrations resulted in greater bacterial inactivation. Many reports have indicated that MgO nanoparticles have better activity towards gram-positive bacteria than towards gramnegative bacteria. The reason is probably due to the difference in cell membrane structure (Fig. 4). The cell wall of gram-positive bacteria (E. coli) consists primarily of thin layers of lipid A, lipopolysaccharide, and peptidoglycan, but that of gram-negative bacteria S. aureus consists of only a peptidoglycan layer. Membrane functions, activity of enzymes associated with the membrane, and maintenance of cell integrity depend on the structure of the cell surface (Espitia et al., 2012). Therefore, E. coli shows a stronger resistance to MgO nanoparticles, compared to S. aureus (Yim et al., 2006). The findings are similar to the antibacterial activity of Ag nanoparticles against gram-positive and gram-negative bacteria. Yoon et al. (2007) observed that B. subtilis was more sensitive than E. coli to Ag nanoparticles, meaning that E. coli was more resistant to nanoparticles than B. subtilis was. The lower sensitivities of E. coli as compared to B. subtilis was ascribed to the fact that the outer membrane of gram-negative bacteria such as E. coli is predominantly constructed from tightly packed lipopolysaccharide (LPS) molecules, which provide an effective barrier against Ag nanoparticles.

Doping is a widely studied method for the modification of nanoparticles (Lin et al., 2009; Yamamoto et al., 2000; Manna, 2012). Yamamoto et al. (2000) studied the change of antibacterial characteristics with the doping amount of ZnO in MgO-ZnO solid solution. The results showed that, with increasing doping amount of ZnO in MgO-ZnO solid solution, a decrease in the antibacterial activity against E. coli and S. aureus was observed. The pH in physiological saline at the powder concentration of 2.5 mg/mL showed an alkali region above 10.0, and decreased with the increase of ZnO amount in MgO-ZnO solution. The reason for the decrease in antibacterial activity may be the decrease of the stability of  $O_2^{-1}$ generated at the surface of the solid-solution and the decrease of pH value in the medium.



Figure 4: Membrane structure of gram-positive and gram-negative bacteria (reproduced with permission from Espitia *et al.*, 2012).

Avanzato *et al.* (2009) investigated the antibacterial activity of magnesium oxide-germanium oxide composite powder. The prepared nano-composite powder showed good bactericidal activity toward both gram-negative (*E. coli*) as well as gram-positive bacteria (*S. aureus*), though they were more efficient against gram-positive bacteria. The results showed that nanocomposite powders were more effective against *S. aureus* than *E. coli* at lower concentrations. At higher concentrations (>5 mg/mL), the growth of bacteria was almost completely inhibited (>95 %) in both cases. The minimal inhibitory concentration (MIC) for *S. aureus* was found to be 0.05 mg/mL whereas that of *E. coli* was found to be 0.25 mg/mL.

# ANTIBACTERIAL MECHANISM OF MgO NANOPARTICLES

The exact antibacterial mechanism of MgO nanoparticles is still unknown. A number of mechanisms, such as the formation of reactive oxygen species (ROS), the interaction of nanoparticles with bacteria, subsequently damaging the bacterial cell, and an alkaline effect have been proposed to explain the antibacterial mechanism of MgO nanoparticles. Several similar mechanisms have been proposed to explain the inhibitory effect of silver nanoparticles on bacteria. Silver has long been known to cause microbial inhibition. The antibacterial mechanisms of silver include induction of oxidative stress due to generation of ROS, which may cause the degradation of the membrane structure of the cell. Release of ions from the surface of nanoparticles has been reported to cause bacterial death due to binding to cell membrane (Emamifar et al., 2011; Kim et al., 2007).

Many studies have indicated that the antibacterial mechanism of MgO nanoparticles is due to the formation of ROS such as superoxide anion  $(O_2^{-})$  (Huang et al., 2005 a, b; Lin et al., 2005; Yamamoto et al., 2010; Yamamoto et al., 2001). It has been reported that the increase of the surface area of MgO particles leads to an increase of the  $O_2^-$  concentration in solution and thus results in a more effective destruction of the cell wall of the bacteria. However, when the particle size of MgO is below 15 nm, the aggregation effect becomes very significant due to the very high surface energy of the particles. The large size of aggregated MgO inhibits the interaction with bacteria and particles so that the bactericidal efficiency becomes lower (Sawai et al., 2000; Yamamoto et al., 2000). Hewitt et al. (2001) reported that the enhancement of the antibacterial activity of MgO nanopowder against E. coli was due to the generation of a large amount of  $O_2^-$  by the surface of MgO powder. Recently, Krishnamoorthy et al. (2012) evaluated the antibacterial activity of MgO nanoparticles against the gram-negative bacteria E. coli and Pseudomonas aeruginosa (P. aeruginosa), as well as the grampositive bacterium S. aureus. MgO nanoparticles exhibited antibacterial activity with MIC of 500 µg/mL against E. coli and 1000 µg/mL for P. aeruginosa and S. aureus. It was suggested that the mechanism of the antibacterial activity of MgO nanoparticles may be lipid peroxidation and ROS due to the presence of defects of oxygen vacancy at the surface of the nanoparticles.

The interaction of MgO nanoparticles with bacteria, subsequently damaging the bacterial surface, has been proposed to explain the antibacterial activity of MgO nanoparticles. Stoimenov *et al.* (2002) suggested that the cell death was caused by the electrostatic interaction between the bacteria surface and MgO nanoparticles. Peter *et al.* (2002) and Makhluf *et al.* (2005) demonstrated that nano-MgO exhibited high activity against bacteria due to the interaction of particles and bacteria. It was found that nano-MgO particles could take up halogen gases due to the defect nature of their surface and its positive charge, which resulted in a strong interaction with bacteria, which are negatively charged (Stoimenov *et al.*, 2002).

The alkaline effect has been considered as another primary factor in the antibacterial action of MgO nanoparticles (Sawai *et al.*, 2001; Yamamoto *et al.*, 2000). Sawai *et al.* (1997) proposed that the possible antibacterial mechanism was the adsorption of water moisture on the MgO nanoparticle surfaces, which could form a thin water layer around the particles. The local pH of this thin water layer formed around the nanoparticles might be much higher than its equilibrium value in solution. When the nanoparticles are in contact with the bacteria, the high pH in this thin surface water layer could damage the membrane, resulting in cells death.

## CONCLUSIONS

MgO nanoparticles are a promising antibacterial agent due to their high resistance to harsh processing conditions. Many synthetic methods, such as the solgel method, hydrothermal method and micro-emulsion method, have been used to prepare MgO nanoparticles. The hydrothermal method has been given more attention due to the simplicity. The antibacterial activity of MgO nanoparticles is size and concentration dependent. Although the exact antibacterial mechanism of MgO nanoparticles is not clear, three main antibacterial mechanisms have been proposed, such as the formation of ROS, the interaction of nanoparticles with bacteria, subsequently damaging the bacterial cell, and an alkaline effect. In the future, more research should be focused on the preparation of MgO nanoparticles with low cost and studies of the antibacterial mechanism of MgO nanoparticles. Also, more studies should be carried out on the activity of MgO nanoparticles towards other microorganism species.

#### REFERENCES

Al-Gaashani, R., Radiman, S., Al-Douri, Y., Tabet, N. and Daud, A. R., Investigation of the optical properties of Mg(OH)<sub>2</sub> and MgO nanostructures obtained by microwave-assisted methods. Journal of Alloys and Compounds, 52, 71-76 (2012).

- Alvarado, E., Torres-Martinez, L. M., Fuentes, A. F. and Quintana, P., Preparation and characterization of MgO powders obtained from different magnesium salt and the mineral dolomite. Polyhedron, 19, 2345-2351 (2000).
- An, Y., Zhang, K., Wang, F., Lin, L. and Guo, H., Removal of organic matters and bacteria by nano-MgO/GAC system. Desalination, 281, 30-34 (2011).
- Aslan, A. and Geddes, C. D., Wavelengh-rationmetric Plasmon light scattering-based immunoassays. Plasmonics, 4, 267-272 (2009).
- Avanzato, C. T., Follieri, J. M. and Banerjee, I. A., Biomimetic synthesis and antibacterial characteristics of magnesium oxide-germanium dioxide nanocomposite powders. Journal of Composite Materials, 43, 897-910 (2009).
- Bertinetti, L., Drouet, C., Combes, C., Rey, C., Tampieri, A., Coluccia, S. and Martra, G., Surface characteristics of nanocrystalline apatites: Effect of MgO surface enrichment on morphology, surface hydration species, and cationic environments. Langmuir, 25, 5647-5654 (2009).
- Bhatte, K. D., Sawant, D. N., Watile, R. A. and Bhanage, B. M., A rapid, one step microwave assisted synthesis of nanosize zinc oxide. Materials Letters, 69, 66-68 (2012).
- Bokhimi, A. M., Crystalline structure of MgO prepared by the sol-gel technique with different hydrolysis catalysis. Journal of Solid State Chemistry, 115, 411-415 (1995).
- Bokhimi, X., Morales, A., Porrtilla, M. and Garcia-Ruiz, A., Hydroxides as precursors of nanocrystalline oxides. Nanostructured Materials, 12, 589-592 (1999).
- Boubeta, C. M., Bacells, L., Cristofol, R., Sanfeliu, C., Rodriguez, E., Weissleder, R., Piedrafita, S., Simeonidis, K., Angelakeris, M., Sandiumenge, F., Calleja, A., Casas, L., Monty, C. and Martinez, B., Self-assembled multifunctional Fe/MgO nanospheres for magnetic resonance imaging and hyperthermia. Nanomedicine, 6, 362-370 (2010).
- Camtakan, Z., Erenturk, S. and Yusan, S., Magnesium oxide nanoparticles: Preparation, characterization, and uranium sorption properties. Environmental Progress & Sustainable Energy, 31, 536-543 (2012).
- Chen, G. R., Xu, S. H. and Yang, J., The study of the preparing of nanometer MgO powder in the stearic acid gel method. Journal of Functional Materials, 35, 521-523 (2002).
- Di, D. R., He, Z. Z., Sun, Z. Q. and Liu, J., A new

nano-cryosurgical modality for tumor treatment using biodegradable MgO nanoparticles. Nanomedicine, 8, 1233-1241 (2012).

- Eastoe, J., Hollamby, M. J. and Hudson, L., Recent advances in nanoparticle synthesis with reversed micelles. Advances in Colloid and Interface Science, 128-130, 5-15 (2006).
- Emamifar, A., Kadivar, M., Shahedi, M. and Solaimanianzad, S., Effect of nanocomposite packaging containing Ag and ZnO on inactivation of *Lactobacillus plantarum* in orange juice. Food Control, 22, 408-413 (2011).
- Esmaeili, E., Khodadadi, A. and Mortazavi, Y., Microwave-induced combustion process variables for MgO nanoparticles synthesis using polyethylene glycol and sorbitol. Journal of the European Ceramic Society, 29, 1061-1068 (2009).
- Espitia, P. J. P., Soares, N. F. F., Coimbra, J. S. R., Andrade, N. J., Cruz, R. S. and Medreiros, E. A. A., Zinc oxide nanoparticles: Synthesis, antimicrobial activity and food packaging applications. Food Bioprocess Technology, 5, 1447-1464 (2012).
- Fang, M., Chen, J. H., Xu, X. L., Yang, P. H. and Hildebrand, H. F., Antibacterial activities of inorganic agents on six bacteria associated with oral infections by two susceptibility tests. International Journal of Antimicrobial Agents, 27, 513-517 (2006).
- Fedorov, P. P., Tkachenko, E. A., Kuznetsov, S. V., Voronov, V. V. and Lavrishchev, S. V., Preparation of MgO nanoparticles. Inorganic Materials, 43, 502-504 (2007).
- Gandhi, S., Abiramipriya, P., Pooja, N., Jeyakumari, J. J. L., Arasi, A. Y., Dhanalakshmi, V., Gopinathan, M. R. and Anbarasan, R., Synthesis and characterizations of nano sized MgO and its nano composite with poly(vinyl alcohol). Journal of Non-Crystalline Solids, 357, 181-185 (2011).
- Ganguli, A. K., Ganguly, A. and Vaidya, S., Microemulsion-based synthesis of nanocrystalline materials. Chemical Society Reviews, 474-485 (2010).
- Ganguly, A., Trinh, P., Ramanujachary, K. V., Ahmad, T., Mugweru, A. and Ganguli, A. K., Reverse micellar based synthesis of ultrafine MgO nanoparticles (8-10 nm): Characterization and catalytic properties. Journal of Colloid and Interface Science, 353, 137-142 (2011).
- Hewitt, C. J., Bellara, S. T., Andreani, A., Nebe-von-Caron, G. and Mcfarlane, C. M., An evaluation of the antibacterial action of ceramic powder slurries using multiparameter flow cytometry. Biotechnology Letters, 23, 667-675 (2001).
- Huang, L., Li, D. Q., Lin, Y. J., Evans, D. G., Duan, X., Influence of nano-MgO particle size on bacte-

ricidal action against *Bacillus subtilis var. niger*. Chinese Science Bulletin, 50, 514-519 (2005).

- Huang, L., Li, D. Q., Lin, Y. J., Wei, M., Evans, D. G., Duan, X., Controllable preparation of nano-MgO and investigation of its bactericidal properties. Journal of Inorganic Biochemistry, 99, 986-993 (2005).
- Huang, Z., Maness, P. C., Blakee, D. M., Wolfrum, E. J., Smoliski, S. L. and Jacoby, W. A., Bacterial mode of titanium dioxide photocatalysis. Journal of Photochemistry and Photobiology A: Chemistry, 130, 163-170 (2000).
- Jin, J., Zhang, Z., Ma, H., Lu, X., Chen, J., Zhang, Q., Zhang, H. and Ni, Y., Surface modification of spherical magnesium oxide with ethylene glycol. Materials Letters, 63, 1514-1516 (2009).
- Jin, T. and He, Y. P., Antibacterial activities of magnesium oxide (MgO) nanoparticles against foodborne pathogens. Journal of Nanoparticles Research, 13, 6877-6885 (2011).
- Jiu, J., Kurumada, K. I., Tanigaki, M., Adachi, M., Yoshikawa, S., Preparation of nanoporous MgO using gel as structure-direct template. Materials Letters, 58, 44-47 (2003).
- Jiu, J. P., Li, L. P., Ge, Y., Zhang, S. R., Tu, F., Hua, Z. R. and Nie, L., The preparation of MgO nanoparticles protected by polymer. Chinese Journal of Inorganic Chemistry, 17, 361-365 (2001).
- Jones, N., Ray, B., Koodali, R. T. and Manna, A. C., Antibacterial activity of ZnO nanoparticles suspensions on a broad spectrum of microorganisms. FEMS Microbiology Letters, 279, 71-76 (2008).
- Jung, H. S., Lee, J. K., Kim, J. Y. and Hong, K. S., Crystallization behaviors of nanosized MgO particles from magnesium alkoxides. Journal of Colloid and Interface Science, 259, 127-132 (2003).
- Jung, H. S., Lee, J. K., Kim, J. Y. and Hong, K. S., Synthesis of nano-sized MgO particle and thin film from diethanolamine-stablized magnesiummethoxide. Journal of Solid State Chemistry, 175, 278-283 (2003).
- Jung, W. K., Koo, H. C., Kim, K. W., Shin, S., Kim, S. H. and Park, Y. H., Antibacterial activity and mechanism of action of the silver ion in *Staphylococcus aureus* and *Escherichia coli*. Applied and Environmental Microbiology, 74, 2171-2178 (2008).
- Khairallah, F. and Glisenti, A., Synthesis, characterization and reactivity study of nanoscale magnesium oxide. Journal of Molecular Catalysis A: Chemical, 274, 137-147 (2007).
- Kim, J. Y., Jung, H. S. and Hong, K. S., Effects of acetic acid on the crystallization temperature of sol-gel-derived MgO nano-powders and thin films. Journal of the American Ceramic Society,

88, 784-787 (2005).

- Kim, Y. M., Kuk, E., Yu, K. N., Kim, J. H., Park, S. J. and Lee, H. J., Antimicrobial effects of silver nanoparticles. Nanomedicine: Nanotechnology, Biology, and Medicine, 3, 95-101 (2007).
- Klabunde, K. J., Stark, J., Koper, O., Mohs, C., Park, D. G., Decker, S., Jiang, Y., Lagadic, I. and Zhang, D., Nanocrystals as stoichiometric reagents with unique surface chemistry. The Journal of Physical Chemistry, 100, 12142-12153 (1996).
- Koper, O. B., Lagadic, I., Volodin, A. and Klabunde, K. J., Alkaline-earth oxide nanoparticles obtained by aerogel methods. Characterization and rational for unexpectedly high surface chemical reactivities. Chemistry of Materials, 9, 2468-2480 (1997).
- Krishnamoorthy, K., Manivannan, G., Kim, S. J., Jeyasubramanian, K. and Premanathan, M., Antibacterial activity of MgO nanoparticles based on lipid peroxidation by oxygen vacancy. Journal of Nanoparticles Research, 14, 1063 (2012).
- Kumar, A. and Kumar, J., On the synthesis and optical absorption studies of nano-size magnesium oxide powder. Journal of Physics and Chemistry of Solids, 69, 2764-2772 (2008).
- Kumar, A., Vemula, P. K., Ajayan, P. M. and John, G., Silver-nanoparticle-embedded antimicrobial paints based on vegetable oil. Nature Materials, 7, 236-241 (2008).
- Li, Y., Leung, P., Yao, L., Song, Q. W. and Newton, E., Antimicrobial effect of surgical masks coated with nanoparticles. Journal of Hospital Infection, 62, 58-63 (2006).
- Li, Y. J., Li, D. Q., Wang, G., Huang, L. and Duan, X., Preparation and bactericidal property of MgO nanoparticles on γ-Al<sub>2</sub>O<sub>3</sub>. Journal of Materials Science: Materials in Medicine, 16, 53-56 (2005).
- Lin, Y. J., Xu, X. Y., Huang, L., Evans, D. G. and Li, D. Q., Bactericidal properties of ZnO-Al<sub>2</sub>O<sub>3</sub> composites formed from layered double hydroxide precursors. Journal of Materials Science: Materials in Medicine, 20, 591-595 (2009).
- Lopez, T., Gomez, R., Navarrete, J. and Lopez-Salinas, E., Evidence for Lewis and Bronsted acid sites on MgO obtained by sol-gel. Journal of Sol-Gel Science and Technology, 13, 1043-1047 (1998).
- Makhluf, S., Dror, R., Nitzan, Y., Abramovich, Y., Jelinek, R. and Gedanken, A., Microwave-assisted synthesis of nanocrystalline MgO and its use as a bacteriocide. Advanced Functional Materials, 15, 1708-1715 (2005).
- Manna, A. C., Synthesis, Characterization, and Antimicrobial Activity of Zinc Oxide Nanoparticles. In Cioffi, N. and Rai, M. (Eds.), Nano-Antimicrobials: Progress and Prospects, Berlin: Springer

Press, pp. 151-180 (2012).

- Mastuli, M. S., Ansari, N. S., Nawawi, M. A. and Mahat, A. M., Effects of cationic surfactant in sol-gel synthesis of nano sized magnesium oxide. APCBEE Procedia, 3, 93-98 (2012).
- Mel'gunov, M. S., Fenelonov, V. B., Mel'gunova, E. A., Bedilo, A. F. and Klabunde, K. J., Textural changes during topochemical decomposition of nanocrystalline Mg(OH)<sub>2</sub> to MgO. The Journal of Physical Chemistry B, 107, 2427-2434 (2003).
- Meshkani, F. and Rezaei, M., Effect of process parameters on the synthesis of nanocrystalline magnesium oxide with high surface area and platelike shape by surfactant assistanted precipitation method. Powder Technology, 199, 144-148 (2010).
- Meshkani, F. and Rezaei, M., Facile synthesis of nanocrystalline magnesium oxide with high surface area. Powder Technology, 196, 85-88 (2009).
- Mirzaei, H. and Davoodnia, A., Microwave assisted sol-gel synthesis of MgO nanoparticles and their catalytic activity in the synthesis of hantzsch 1, 4dihydropyridines. Chinese Journal of Catalysis, 33, 1502-1507 (2012).
- Moghaddam, F. M. and Saeisian, H., Controlled microwave-assisted synthesis of ZnO nanopowder and its catalytic activity for O-acylation of alcohol and phenol. Materials Science and Engineering: B, 139, 265-269 (2007).
- Morris, J. G., How safe is our food? Emerging Infectious Diseases, 17, 126-128 (2011).
- Nel, A., Xia, T., Madler, L. and Li, N., Toxic potential of materials at the nanolevel. Science, 311, 622-627 (2006).
- Nishioka, M., Miyakawa, M., Kataoka, H., Koda, H., Sato, K. and Suzuki, T. M., Continuous synthesis of monodispersed silver nanoparticles using a homogenous heating microwave reactor system. Nanoscale, 3, 2621-2626 (2011).
- Nishioka, M., Miyakawa, M., Kataoka, H., Koda, H., Sato, K. and Suzuki, T. M., Facile and continuous synthesis of Ag-SiO<sub>2</sub> core-shell nanoparticles by a flow reactor system assisted with homogeneous microwave heating. Chemistry Letters, 40, 1204-1206 (2011).
- Ouraipryvan, P., Sreethawong, T. and Chavadej, S., Synthesis crystalline MgO nanoparticle with mesporous-assembled structure via a surfactant-modified sol-gel process. Materials Letters, 63, 1862-1865 (2009).
- Pal, S., Tak, Y. K. and Song, J. M., Does the antibacterial activity of silver nanoparticles depend on the shape of the nanoparticles? A study of the gramnegative bacterium *Escherichia coli*. Applied and Environmental Microbiology, 73, 1712-1720 (2007).

- Parida, K. M. and Parija, S., Photocatalytic degradation of phenol under solar radiation using microwave irradiated zinc oxide. Solar Energy, 80, 1048-1054 (2006).
- Peter, K. S., Rosalyn, L., George, L. M. and Klabunde, J. K., Metal oxide nanoparticles as bactericidal agents. Langmuir, 6679-6686 (2002).
- Portillo, R., Lopez, T. and Gomez, R., Magnesia synthesis via sol-gel: Structure and reactivity. Langmuir, 12, 40-44 (1996).
- Raghupati, R. K., Koodali, R. T. and Manna, A. C., Size-dependent bacterial growth inhibition and mechanism of antibacterial activity of zinc oxide nanoparticles. Langmuir, 27, 4020-4028 (2011).
- Ranjan, R., Vaidya, S., Thaplyal, P., Qamar, M., Ahmad, T., Antonelli Jr., A. M., Ramanujachary, K. V., Lofland, S. E. and Ganguli, A. K., Controlling the size, morphology, and aspect ratio of nanostructure using reverse micelles: A case study of copper oxalate monohydrate. Langmuir, 25, 6469-6475 (2009).
- Reddy, M. M. B., Ashoka, S., Chandrappa, G. T. and Pasha, M. A., Nano-MgO: An efficient catalyst for the synthesis of formamides from amines and formic acid under MWI. Catalysis Letters, 138, 82-87 (2010).
- Roselli, M., Finamore, A., Garaguso, I., Britti, M. S. and Mengheri, E., Zinc oxide protects cultured enterocytes from the damage induced by *Escherichia coli*. Journal of Nutrition, 133, 4077-4082 (2003).
- Sawai, J., Quantitative evaluation of antibacterial activities of metallic oxide powders (ZnO, MgO and CaO) by an indirect conductimetric assay. Journal of Microbiological Methods, 54, 177-182 (2003).
- Sawai, J., Igarashi, H., Hasimoto, A., Kokugan, T. and Shimizu, M., Evaluation of growth inhibitory effect of ceramic powder slurry on bacteria by conductance method. Journal of Chemical Engineering of Japan, 28, 288-293 (1995).
- Sawai, J., Kojima, H., Igarashi, H., Hasimoto, A., Shoji, S., Sawaki, T., Hakoda, A., Kawada, E., Kokugan, T. and Shimizu, M., Antibacterial characteristics of magnesium oxide powder. World Journal of Microbiology and Biotechnology, 16, 187-194 (2000).
- Sawai, J., Kojima, H., Igarashi, H., Hasimoto, A., Shoji, S. and Shimizu, M., Bactericidal action of calcium oxide powder. Transactions of the Materials Research Society of Japan, 24, 667-670 (1999).
- Sawai, J., Kojima, H., Igarashi, H., Hasimoto, A., Shoji, S., Takehara, A., Sawaki, T., Kokugan, T.

and Shimizu, M., *Escherichia coli* damage by ceramic powder slurries. Journal of Chemical Engineering of Japan, 30, 1034-1039 (1997).

- Sawai, J., Shoji, S., Igarashi, H., Hashimoto, A., Kokugan, T., Shimizu, M. and Kojima, H., Hydrogen peroxide as an antibacterial factor in zinc oxide powder slurry. Journal of Fermentation of Bioengineering, 86, 521-522 (1998).
- Sawai, J., Shuga, S. and Kojima, H., Kinetic analysis of death of bacteria in CaO powder slurry. International Biodeterioration & Biodegradation, 47, 23-26 (2001).
- Selvam, N. C. S., Kumar, R. T., Kennedy, L. J. and Vijaya, J. J., Comparative study of microwave and conventional methods for the preparation and optical properties of novel MgO-micro and nanostructures. Journal of Alloys and Compounds, 509, 9809-9815 (2011).
- Shivastava, S., Bera, T., Roy, A., Singh, G., Ramachandrarao, P. and Dash, D., Characterization of enhanced antibacterial effects of novel silver nanoparticles. Nantotechnology, 18, 1-9 (2007).
- Stark, J. V., Park, D. G. and Lagadic, I., Nanoscale metal oxide particles/clusters as chemical reagents. Unique surface chemistry on magnesium oxide as shown by enhanced adsorption of acid gas (sulfur dioxide and carbon dioxide) and pressure dependence. Chemistry of Materials, 8, 1904-1912 (1996).
- Stengl, V., Bakardjieva, S., Marikova, M., Subrt, J., Oplustil, F. and Olsanska, M., Aerogel nanoscale magnesium oxides as a destructive sorbent for toxic chemical agents. Central European Journal of Chemistry, 2, 16-33 (2004).
- Stoimenov, P. K., Klinger, R. L., Marchin, G. L. and Klabunde, K. J., Metal oxide nanoparticles as bactericidal agents. Langmuir, 18, 6679-6686 (2002).
- Subramania, A., Kumar, G. V., Sathiya Priya, A. R. and Vasudevan, T., Polyol-mediated thermolysis process for the synthesis of MgO nanoparticles and nanowires. Nanotechnology, 18, 225601, (1-5) (2007).
- Sundrarajan, M., Suresh, J. and Gandhi, R. R., A comparative study on antibacterial properties of MgO nanoparticles prepared under different calcination temperature. Digest Journal of Nanomaterials and Biostructures, 7, 983-989 (2012).
- Sutradhar, N., Sinhamahapatra, A., Roy, B., Bajaj, H. C., Mukhopadhyay, I. and Panda, A. B., Preparation of MgO nano-rods with strong catalytic activity via hydrated basic magnesium carbonates. Materials Research Bulletin, 46, 2163-2167 (2011).

- Suzuki, M., Kagawa, M. and Syonoetal Y., Synthesis of ultrafine single-component oxide particles by the spray ICP technique. Journal of Material Science, 27, 679-684 (1992).
- Takahashi, N., Simple and rapid synthesis of MgO with nano-cube shape by means of a domestic microwave oven. Solid State Sciences, 9, 722-724 (2007).
- Tang, Z. X., Fang, X. J., Zhang, Z. L., Zhou, T., Zhang, X. Y. and Shi, L. E., Nano MgO as antibacterial agent: Preparation and characteristics. Brazilian Journal of Chemical Engineering, 29, 775-781 (2012).
- Tang, Z. X. and Shi, L. E., Preparation of nano-MgO using ultrasonic method and its characteristics. Eclética Química, 33, 15-20 (2008).
- Vaidya, S., Rastogi, P., Agarwal, S., Gupta, S. K., Ahmad, T., Antonelli, Jr. A. M., Ramanujachary, K. V., Lofland, S. E. and Ganguli, A. K., Nanospheres, nanocubes, and nanorods of nickel oxalate: Control of shape and size by surfactant solvent. The Journal of Physical Chemistry C, 112, 12610-12615 (2008).
- Wani, A. H. and Shah, M. A., A unique and profound effect of MgO and ZnO nanoparticles on some plant pathogenic fungi. Journal of Applied Pharmaceutical Science, 2, 40-44 (2012).
- Xu, X. M., Preparation and characterization of nanometer magnesia powder by electrochemical precipitation. Inorganic Chemicals Industry, 38, 32-34 (2006).
- Yamamoto, O., Fukuda, T., Kimata, M., Sawai, J. and Sasamoto, T., Antibacterial characteristics of MgO-mounted spherical carbons prepared by carbonization of ion-exchanged resin. Journal of the Ceramic Society of Japan, 109, 363-365 (2001).
- Yamamoto, O., Ohira, T., Alvarez, K. and Fukuda, M., Antibacterial characteristics of CaCO<sub>3</sub>-MgO

composites. Materials Science and Engineering B, 173, 208-212 (2010).

- Yamamoto, O., Sawai, J. and Sasamoto, T., Change in antibacterial characteristics with doping amount of ZnO in MgO-ZnO solid solution. International Journal of Inorganic Materials, 2, 451-454 (2000).
- Yim, G., Wang, H. H. and Davies, J., The truth about antibiotics. International Journal of Medical Microbiology, 296, 163-170 (2006).
- Yoon, K. Y. H., Park, J. H. and Hwang, J., Susceptibility constants of *Escherichia coli* and *Bacillus subtilis* to silver and copper nanoparticles. Science of the Total Environment, 373, 572-575 (2007).
- Zhang, K., An, Y., Wang, F., Lin, L. and Guo, H., Experimental investigation on water treatment by the combined nano MgO-nanofiltration technique. Water Science and Technology, 63, 2542-2546 (2011).
- Zhang, J., Study on preparing nanometer-sized MgO by homogeneous precipitation. Method, Materials, 30, 193-194 (1999).
- Zhou, J., Yang, S. and Yu, J., Facile fabrication of mesoporous MgO microspheres and their enhanced adsorption performance for phosphate from aqueous solutions. Colloids and Surface A: Physicochemical and Engineering Aspects, 379, 102-108 (2011).
- Zhu, Y. X., Zeng, R. J., Liu, X. J., Zhang, H., Pan, R., Zhou, X. L. and Zhang, Y., Preparation and characterization of MgO nanopowder. Journal of Xiamen University (Nature Science), 40, 1256-1258 (2001).
- Znaidi, L., Chhor, K. and Pommier, C., Batch and semi-continuous synthesis of magnesium oxide powders from hydrolysis and supercritical treatment of Mg(OCH<sub>3</sub>)<sub>2</sub>. Materials Research Bulletin, 31, 1527-1535 (1996).