ISSN 0104-6632 Printed in Brazil www.abeq.org.br/bjche

Vol. 28, No. 01, pp. 89 - 94, January - March, 2011

PRECIPITATION OF AMORPHOUS SiO₂ PARTICLES AND THEIR PROPERTIES

S. Musić^{1*}, N. Filipović-Vinceković¹ and L. Sekovanić²

¹Ruđer Bošković Institute, Phone: + 385 1 4561 094, Fax: + 385 1 4680 107, P.O. Box 180, HR-10002 Zagreb, Croatia. E-mail: music@irb.hr

²Faculty of Geotechnical Engineering, University of Zagreb, Varaždin, Croatia.

(Submitted: April 20, 2010; Revised: September 23, 2010; Accepted: October 5, 2010)

Abstract - The experimental conditions were optimized for the synthesis of amorphous SiO₂ particles by the reaction of neutralization of sodium silicate solution with H_2SO_4 solution. Amorphous SiO₂ particles were characterized by XRD, FT-IR, FE-SEM, EDS and microelectrophoresis. The amorphous peak was located at $2\theta = 21.8^{\circ}$ in the XRD pattern. Primary SiO₂ particles were ~ 15 to ~ 30 nm in size and they aggregated into bigger particles. Amorphous SiO₂ particles showed a specific surface area up to 130 m²g⁻¹, dependent on the parameters of the precipitation process. The EDS spectrum of amorphous SiO₂ particles did not show contamination with sulfate or other ions, which cannot be excluded in traces. $pH_{zpc} = 1.7$ was obtained by microelectrophoresis.

Keywords: Precipitated SiO₂; XRD; FT-IR; FE-SEM; EDS; Microelectrophoresis

INTRODUCTION

Precipitated SiO₂ (silica) has found various applications as filler in rubber and plastics, absorbent, drying powder, substrate for catalysts, anticorrosion agent, etc. Generally, precipitated SiO₂ can be produced by mixing of aqueous solutions of sodium metasilicate and a mineral acid (Winvall, 1984). For example, Schlomach and Kind (2004) precipitated silica by simply adding 50% sulphuric acid into sodium metasilicate solution. The primary silica particles had a uniform size at 22.7 nm. Jesionowski (2002) investigated the precipitation of silica from sodium metasilicate solution using hydrochloric acid. Nonionic surfactants, polydisperse mono(4nonylphenyl)polyoxyethylene glycol ethers were used as emulsifiers. Spherical silica particles were obtained by using the ultrasonic bath. The precipitated silica had a specific surface area in the interval of 120-260 m^2/g . Also, Jesionowski (2001) investigated precipitation of silica from sodium metasilicate and sulfuric acid in emulsions. Cai et al. (2009) used carbon dioxide to precipitate silica from sodium metasilicate solution. The size of the aggregated SiO_2 particles obtained by dynamic light scattering was about 160 nm. The production of nanofibrillar silica (amorphous) from natural chrysotile asbestos was also investigated. (Wang et al. 2006; Liu et al. 2007).

The properties of precipitated SiO_2 depend strongly on the conditions of its synthesis, such as the synthesis temperature, time of precipitation, pH, addition of coagulant, and modes of washing and drying. These factors influence the size of the SiO_2 particles, their aggregation and specific surface area. The optimization of the properties of precipitated SiO_2 is not an easy task.

In the present work we focus on the precipitation of amorphous SiO_2 . The optimization of the synthesis factors was achieved, so that precipitated SiO_2 produced as described in the present work can be used for further academic investigations, and also as a valuable commercial product.

^{*}To whom correspondence should be addressed

EXPERIMENTAL

Synthesis of Precipitated SiO₂

The commercial aqueous solution of sodium silicate (water glass) having a chemical composition in the range 7.8 - 8.5% Na₂O, 24.8 - 27% SiO₂, 64 -67% H₂O, and specific weight 1.35 - 1.36 g mL⁻¹ was used. After filtration, the sodium silicate solution was diluted in distilled water in the ratio of 1:4 by volume. A concentrated H₂SO₄ solution was diluted in distilled water in the ratio of 1:10 by volume. This H₂SO₄ solution was used to neutralize the silicate component by addition at a constant speed and strong mixing of the precipitation system using a high energy disperser. The speed of adding the dilute H₂SO₄ solution depended on the temperature. In the temperature interval of 80-90°C, the speed of adding H₂SO₄ was 120 - 50 min. The dilute H₂SO₄ solution was added up to pH 9 - 9.5. The pH was measured at room temperature. At this pH and a temperature of 80-90°C, the precipitated system was additionally heated for 42 - 17 min. This was followed by cooling the precipitated system to room temperature. Then, dilute H₂SO₄ solution was added up to pH 5.5. At this pH, NaCl solution was added over 30 min. The concentration of NaCl varied between 1 and 5 g/L of the reaction mixture.

Coagulated SiO₂ was separated from the mother liquor and subsequently washed with distilled water until there was a negative reaction for sulfate ions, as controlled with 0.1 M BaCl₂ solution. The separated cake was dried in a cyclone dryer.

Instrumentation

pH values were measured with a pHM-26 instrument and a combined glass electrode with an operating range of up to pH \sim 14, both manufactured by *Radiometer* (Denmark).

The X-ray powder diffraction pattern was recorded using an APD 2000 diffractometer manufactured by *ItalStructures* (Riva Del Garda, Italy).

The Fourier transform IR spectrum was recorded using a *Perkin-Elmer* spectrometer (Model 2000). The specimen was pressed using a spectroscopically pure KBr matrix.

The BET measurement was performed using a *FlowSorb* II 2300 surface area analyzer (*Micromeritics*, Norcross, GA, USA).

Electrophoretic mobilities were measured using a microelectrophoresis apparatus manufactured by *Rank Brothers*, Cambridge, U.K.

A thermal field emission scanning electron microscope (FE-SEM, model JSM-7000F) manufactured by *Jeol Ltd.* (Japan) was used. FE-SEM was linked to an EDS/INCA 350 (energy dispersive X-ray analyzer) manufactured by *Oxford Instruments Ltd.* (UK). Sample was not coated with an electrically conductive layer.

RESULTS AND DISCUSSION

Fig. 1 shows an X-ray powder diffraction pattern of precipitated SiO₂. An amorphous peak with the equivalent Bragg angle at $2\theta = 21.8^{\circ}$ was recorded. Martinez et al. (2006) prepared amorphous SiO_2 by the sol-gel procedure, subjected it to thermal treatment, then analyzed it using the Rietveld refinement. In their work, an amorphous peak was centered at $2\theta = 23^{\circ}$. With an increased heating temperature, this peak was shifted to lower 20 values. Depending on the molar ratio (R) of water to TEOS (R = 5 or 11.66) and the heating temperature, the amorphous structure transformed to guartz-like or cristobalite-like structures. Zhang et al. (2008) also recorded one broadened XRD peak for amorphous silica centered at a 2Θ value close to our measurement. Only this XRD peak, corresponding to the amorphous phase, was present upon heating the starting material up to 800°C. Upon heating amorphous silica at 1000°C, tetragonal αcrystobalite and a small fraction of monoclinic tridymite were obtained.



Figure 1: X-ray powder pattern of precipitated SiO₂ with a characteristic amorphous peak

Jesionowski and Krysztafkiewicz (1999) precipitated SiO_2 using the reaction of sodium

silicate with dilute HCl, H₂SO₄ or CO₂ in alcoholcontaining media. Dispersibility and size of the SiO₂ particles depended on the nature of the alcohol added. In the presence of isopropanol, SiO₂ particles were 525 nm in size, with a tendency to form aggregates 1340 nm in size. The precipitation of SiO_2 in the presence of ethylene glycol yielded particles 112 nm in size, whereas in the presence of glycerine SiO₂ particles 360 nm in size were formed. Pajonk et al. (1995)prepared SiO₂ aerogels using polyethoxydisiloxanes obtained by the reaction of tetraethoxysilane (TEOS) and water in the presence of sulfuric acid. Sol-gel reactions were conducted under acidic, neutral or basic conditions in methanol, ethanol or acetone. Hyeon-Lee et al. (1997) applied the aero-sol-gel procedure to prepare SiO₂ powder with a very high specific surface area, $\sim 400 \text{ m}^2\text{g}^{-1}$. An inverse microemulsion sol-gel procedure was used to prepare SiO₂ particles of colloidal dimensions (Espiard et al. 1995). The sol-gel procedure was also used to prepare porous and spherical SiO₂ particles (Hirose et al. 1994). Spherical SiO₂ particles showed a tendency to increase in size with an increase of ultrasonic energy during the synthesis of these particles (Enomoto et al. 1996).

In the present work, a specific surface area of up to $130 \text{ m}^2\text{g}^{-1}$ could be obtained. This is important, especially if we consider the relative simplicity of the procedure for the production of amorphous SiO₂ as applied in the present work.

Fig. 2 shows FE-SEM images of the amorphous SiO_2 particles at different optical magnifications. The majority of primary SiO_2 particles were ~15 to ~ 30 nm in size. These primary particles showed a tendency to form bigger particles (aggregates). Fig. 3 shows the EDS spectrum of amorphous SiO_2 particles. This spectrum showed only the presence of silicon and oxygen. An excess of oxygen in relation to the stoichiometric ratio Si:O = 1:2 can be attributed to the presence of water and -SiOH groups. The analysis of precipitated SiO_2 showed that it contained 7.63% of



Fig. 5 shows the FT-IR spectrum of precipitated SiO₂. The IR band at 3437 cm⁻¹ is due to the stretching vibration of H2O molecules. Correspondingly, the IR band at 1632 cm⁻¹ is due to the bending vibration of H_2O molecules. The shoulder at 3246 cm⁻¹ could be assigned to the stretching vibrations of Si-OH groups in the structure of amorphous SiO₂. The presence of the Si-OH group is proved as bonded water. The very strong and broad IR band at 1111 cm⁻¹ with a shoulder at 1188 cm⁻¹ is usually assigned to the TO and LO modes of the Si-O-Si asymmetric stretching vibrations. The IR band at 956 cm⁻¹ can be assigned to silanol groups. In the case of alkali silicate glasses, this band is assigned to Si-O stretching vibrations. The IR band at 800 cm⁻¹ can be assigned to Si-O-Si symmetric stretching vibrations, whereas the IR band at 474 cm⁻¹ is due to O-Si-O bending vibrations. Murphy and Grevtak (1979) assigned the IR band at 380 cm⁻¹ to the Si-OH wagging mode. In the present work, the IR band at 380 to 377 cm⁻¹ is recorded as a shoulder at 378 cm⁻¹.



Figure 2: FE-SEM images of precipitated SiO₂ at different optical magnifications (details a and b).

91

Brazilian Journal of Chemical Engineering Vol. 28, No. 01, pp. 89 - 94, January - March, 2011 Short Communication



Figure 3: EDS spectrum of precipitated SiO₂.



Figure 4: Electrophoretic mobility of amorphous SiO₂ particles as a function of the pH of the suspension.

Bock and Su (1970) recorded the IR spectrum of fused silica and compared it with the results of vibrational calculations. For fused silica, the IR bands at 377, 465, 800, 950, 1100 and 1190 cm⁻¹ were recorded. These IR bands also appear in crystalline silica (quartz, crystobalite and tridymite). Of course, the crystalline silicas have more pronounced IR bands with narrower line-widths. Amorphous silica and crystalline silica can really only be distinguished on the basis of measurements in the far-IR region. Vibrational spectra of silica glasses have been studied (Philips, 1987; Tomozawa et al. 2005) and IR spectroscopy used to monitor changes in amorphous SiO₂ during its heating up to 1150°C (Chmel et al. 1990). Innocenzi (2003) used IR spectroscopy to investigate different stages during the sol-gel formation of silica. The FT-IR spectrum shown in Fig. 5 agrees well with the spectrum obtained for amorphous SiO₂ precipitated by the carbonation method (Cai et al. 2009).



Figure 5: FT-IR spectrum of precipitated SiO₂.

CONCLUSION

• Precipitated silica was produced by neutralization of sodium silicate solution (water glass) with H_2SO_4 solution. The synthesis parameters, such as temperature, time of mixing, pH and the amount of coagulant were optimized. Precipitated silica in the form of powder, as obtained with the optimized parameters, could reach a specific surface area of up to 130 m²g⁻¹.

• X-ray powder diffraction of precipitated silica showed one amorphous peak located at $2\theta = 21.8^{\circ}$ and the FT-IR spectrum was typical of that known for amorphous SiO₂.

• FE-SEM inspection showed primary SiO_2 particles ~15 to ~ 30 nm in size. These particles showed a tendency to aggregate (secondary particles).

• The EDS spectrum did not show a contamination of precipitated SiO_2 with sulfate or other ions. "Foreign" ions could be present at the level of traces. Amorphous SiO_2 particles contained "structural" and "free" water (moisture) which were responsible for excess oxygen in these particles. $pH_{zpc} = 1.7$ was determined by microelectrophoretic measurements.

• Properties of precipitated silica produced at the technological level using the same procedure matched those obtained at the laboratory level.

REFERENCES

- Bock, J., Su, G.-J., Interpretation of the infrared spectra of fused silica. J. Amer. Ceram. Soc., 53, p. 69 (1970).
- Cai, X., Hong, R. Y., Wang, L. S., Wang, X. Y., Li, H. Z., Zheng, Y., Wei, D. G., Synthesis of silica powders by pressured carbonation. Chem. Eng. J., 151, p. 380 (2009).
- Chmel, A., Mazurina, E. K., Shashkin, V. S., Vibrational spectra and defect structure of silica prepared by non-organic sol-gel process. J. Non-Crystall. Solids, 122, p. 285 (1990).
- Enomoto, N., Koyano, T., Nakagawa, Z., Effect of ultrasound on synthesis of spherical silica. Ultrasonics Sonochemistry, 3, p. S105 (1996).
- Espiard, P., Guyot, A., Mark, J. E., Surface functionalized colloidal silica particles from an inverse microemulsion sol gel process. J. Inorg. Organometallic Polym., 5, p. 391 (1995).
- Hirose, A., Yamashita, H., Maekawa, T. Synthesis of porous SiO₂ spherical particles by sol-gel methods in W/O emulsion. Analytical Sci. (Japan), 10, p. 737 (1994).

- Hyeon-Lee, J., Beaucage, G., Pratsinis, S. E., Aerosol-gel synthesis of nanostructured silica powders. Chem. Mater., 9, p. 2400 (1997).
- Innocenzi, P., Infrared spectroscopy of sol-gel derived silica-based films: a spectramicrostructure overview. J. Non-Crystall. Solids, 316, p. 309 (2003).
- Jesionowski, T., Krysztafkiewicz, A., Properties of highly dispersed silicas precipitated in an organic medium. J. Dispersion Sci. Technol., 20, p. 1609 (1999).
- Jesionowski. T., Preparation of colloidal silica from sodium metasilicate solution and sulphuric acid in emulsion medium. Colloids & Surfaces A: Physicochem. Eng. Aspects, 190, p. 153 (2001).
- Jesionowski, T. Characterization of silicas precipitated from solution of sodium metasilicate and hydrochloric acid in emulsion medium. Powder Technol., 127, p. 56 (2002).
- Liu, K., Feng, Q., Yang, Y., Zhang, G, Ou, L., Lu, Y., Preparation and characterization of amorphous silica nanowires from natural chrysotile. J. Non-Crystall. Solids, 353, p. 1534 (2007).
- Martinez, J. R., Palomares, S., Ortega-Zarzosa, G., Ruiz, F., Chumakov, Y., Rietveld refinement of amorphous SiO₂ prepared via sol-gel method. Mater. Lett., 60, p. 3526 (2006).
- Murray, C. A., Greytak, T. J., Intrinsic surface phonons in amorphous silica. Phys. Rev., B 20, 3368 (1979).
- Musić, S., Ristić, M., Tonković, M., Sorption of chromium (VI) on hydrous iron-oxides. Z. Wasser, Abwasser-Forsh. 19, p. 186 (1986).
- Musić, S., Ristić, M., Adsorption of trace elements or radionuclides on hydrous iron oxides J. Radioanal. Nucl. Chem., 120, p. 289 (1988).
- Pajonk, G. M., Elaloui, E., Achard, P., Chevalier, B., Chevalier, J. -L., Durant, M., Physical properties of silica gels and aerogels prepared with new polymeric precursors. J. Non-Crystall. Solids, 186, p. 1 (1995).
- Philips, J. C., Structural model of Raman "defect" bands of vitreous silica. Phys. Rev., B 5, p. 6409 (1987).
- Schlomach, J., Kind, M., Investigation of semi-batch precipitation of silica. J. Coll. Interface Sci., 277, p. 316 (2004).
- Tomozawa, M., Hong, J. -W., Ryu, S. -R., Infrared (IR) investigation of the structural changes of silicaglasses with fictive temperature. J. Non-Crystall. Solids, 351, p. 1054 (2005).
- Wang, L., Lu, A., Wang, C., Zheng, X., Zhao, D., Liu, R., Nano-fibriform production of silica from

natural chrysotile. J. Coll. Interface Sci., 295, p. 436 (2006).

- Winyall, M. E., "Silica Gels: Preparation and Properties", in: Applied Industrial Catalysis, 3, p. 43, Academic Press, Inc. (1984).
- Zhang, G., Xu, Y., Xu, D., Wang, D., Xue, Y., Su, W., Pressure-induced crystallization of amorphous SiO₂ with silicon-hydroxy group and the quick synthesis of coesite under lower temperature. High Pressure Res., 28, p. 641 (2008).